

TILE INSTITUTE of AMERICA

1262 Bouquet Circle, Thousand Oaks, California 91362 Telephone: (805) 371-TILE (8453) Facsimile: (805) 371-8455

TIA's Client: 20140815

AquaBella/Main Street Art, Inc.
Mr. Brian L. Streadbeck
450 South Alpine Highway
Alpine, Utah 84004

Telephone: (714) 264-8269 Facsimile: (714) 685-0465
brian@msagallery.com

Tile: **Tahitian** Series, color mottled blue "AZ-606" **Azul Blue** porcelain body glazed.
Nominal size: 6" x 6" x 1/4". Tile made in China.

Conditions: New tiles sent to TILE INSTITUTE of AMERICA in sealed manufacturer's boxes from client above and selected at random.

Report of Test

STAIN RESISTANCE (T-72)


Standard Test Method for Stain Resistance of Ceramic Tile. This method provides the means for establishing whether this tile can resist staining from six commonly used materials, which may appear in tile specifications. The tile samples were prepared as per specifications with the common household materials (each material having one sample covered with a Petri dish and the other uncovered) and left for 24 hours, and then cleaned with Ajax Industrial Cleaner and water.

<u>Sample Tiles</u>	<u>Staining Materials</u>	<u>Observation of Surface Stain</u>	
		<u>Uncovered</u>	<u>Covered</u>
1.	Coca Cola	No Stain	No Stain
2.	Lemon Juice	No Stain	No Stain
3.	Mustard	No Stain	No Stain
4.	Bacon Grease	No Stain	No Stain
5.	Catsup	No Stain	No Stain
6.	Wesson Oil	No Stain	No Stain

Requirements: When tested as described. No evidence of any surface stain remaining and all traces of the staining materials can be washed from the tile's surface.

Test Results: **Pass**

Sincerely,


Gerald M. Halweg, CTC, CSI, TTA.
President/CEO

Date: 11-1-2014