



TILE INSTITUTE of AMERICA

1262 Bouquet Circle, Thousand Oaks, California 91362 Telephone: (805) 371-TILE (8453) Facsimile: (805) 371-8455

TIA's Client: 20160415

AquaBella/Main Street Art, Inc.
Mr. Brian L. Streadbeck
450 South Alpine Highway
Alpine, Utah 84004

Telephone: (714) 264-8269 Facsimile: (714) 685-0465

brian@msagallery.com

Tile: **Night Life Series, multi-colored "NL-1234 Soul" glass body**, mesh back mounted.

Nominal size: 1" x 2" x 1/4" Pattern. Tile made in China.

Conditions: New tiles sent to TILE INSTITUTE of AMERICA from client above and selected at random.

Resistance of Tile to Chemical Substances (ASTM C650)

Procedure: This test method covers a procedure for determining whether, and to what degree, tiles are affected by prolonged exposure to chemical substances. The temperature was controlled at 75±5 °F (24±3 °C) with an exposure time of 24 hours.

Specimens	Substance	Temperature, °F (°C)	Time, hours	Results
1.	10% Hydrochloric Acid	75±5 (24 ± 3)	24	Not affected
1.	10% Potassium Hydroxide	75±5 (24 ± 3)	24	Not affected
2.	10% Hydrochloric Acid	75±5 (24 ± 3)	24	Not affected
2.	10% Potassium Hydroxide	75±5 (24 ± 3)	24	Not affected
3.	10% Hydrochloric Acid	75±5 (24 ± 3)	24	Not affected
3.	10% Potassium Hydroxide	75±5 (24 ± 3)	24	Not affected
4.	10% Hydrochloric Acid	75±5 (24 ± 3)	24	Not affected
4.	10% Potassium Hydroxide	75±5 (24 ± 3)	24	Not affected
5.	10% Hydrochloric Acid	75±5 (24 ± 3)	24	Not affected
5.	10% Potassium Hydroxide	75±5 (24 ± 3)	24	Not affected
6.	10% Hydrochloric Acid	75±5 (24 ± 3)	24	Not affected
6.	10% Potassium Hydroxide	75±5 (24 ± 3)	24	Not affected
7.	10% Hydrochloric Acid	75±5 (24 ± 3)	24	Not affected
7.	10% Potassium Hydroxide	75±5 (24 ± 3)	24	Not affected
8.	10% Hydrochloric Acid	75±5 (24 ± 3)	24	Not affected
8.	10% Potassium Hydroxide	75±5 (24 ± 3)	24	Not affected
9.	10% Hydrochloric Acid	75±5 (24 ± 3)	24	Not affected
9.	10% Potassium Hydroxide	75±5 (24 ± 3)	24	Not affected
10.	10% Hydrochloric Acid	75±5 (24 ± 3)	24	Not affected
10.	10% Potassium Hydroxide	75±5 (24 ± 3)	24	Not affected
11.	10% Hydrochloric Acid	75±5 (24 ± 3)	24	Not affected
11.	10% Potassium Hydroxide	75±5 (24 ± 3)	24	Not affected
12.	10% Hydrochloric Acid	75±5 (24 ± 3)	24	Not affected
12.	10% Potassium Hydroxide	75±5 (24 ± 3)	24	Not affected

Test Results: **Pass**

Sincerely,

Gerald M. Halweg, CTC, CSI, TTA.
President/CEO of TILE INSTITUTE of AMERICA

Date: June 8, 2016