

## TILE INSTITUTE of AMERICA

1262 Bouquet Circle, Thousand Oaks, California 91362 Telephone: (805) 371-TILE (8453) Facsimile: (805) 371-8455

**AquaBella/Main Street Art, Inc.**  
450 South Alpine Highway  
Alpine, Utah 84004

(714) 264-8269  
[brian@msagallery.com](mailto:brian@msagallery.com)

Tile: **Unglazed** Series, color blue "UG-30" **White** porcelain body glazed.  
Nominal size: 2" x 2" x 1/4" (1.850" x 1.850" x 0.225"). Tile made in China.

Conditions: New tiles sent to TILE INSTITUTE of AMERICA in sealed manufacturer's boxes from client above and selected at random.

### Dynamic Coefficient of Friction (ANSI B101.3)


Test Method for Dynamic coefficient of friction testing of Ceramic Tile. This method provides means for establishing measurement of slip resistance of a tile surface which may be required in tile specifications.

Tile Number	Average	Minimum	Maximum
1	0.45	0.31	0.60
2	0.44	0.30	0.59
3	0.49	0.32	0.63
4	0.45	0.31	0.64
Machine Reading 1 Result:	<b>0.46</b>		

Tile Number	Average	Minimum	Maximum
1	0.48	0.36	0.66
2	0.47	0.33	0.63
3	0.43	0.34	0.53
4	0.47	0.35	0.65
Machine Reading 2 Result:	<b>0.46</b>		

**Requirements: When tested as described in ANSI B101.3 tile must yield test values of 0.42 or higher.**

Respectfully Submitted:

  
Gerald M. Halweg, CTC, CSI, TIA.  
President/CEO

Date: 11-7-2014