



# TILE INSTITUTE of AMERICA

1262 Bouquet Circle, Thousand Oaks, California 91362 Telephone: (805) 371-TILE (8453) Facsimile: (805) 371-8453  
23825 15<sup>th</sup> Avenue SE #110, Bothell, Washington 98021 240 Makee Road, Suite PH-A, Honolulu, Hawaii 96815  
[DoctorTile@aol.com](mailto:DoctorTile@aol.com) [DoctorTile1@gmail.com](mailto:DoctorTile1@gmail.com) (805) 444-8453

TIA's Client: 20201228 BS

**Aquabella USA, LLC**  
**Mr. Brian L. Streadbeck**  
**450 South Alpine Highway**  
**Alpine, Utah 84004**

Telephone: (833) 985-2955  
[info@aquabellatile.com](mailto:info@aquabellatile.com)

Tile: **Fjord Series**

FJ-1160 - SERENE 1X1	FJ-1199 - MISTY 1X1	FJ-1298 - SILENT 1X2
FJ-1161 - TRANQUIL 1X1	FJ-1260 - SERENE 1X2	FJ-1299 - MISTY 1X2
FJ-1162 - GRAND 1X1	FJ-1261 - TRANQUIL 1X2	FJ-893 - PEACEFUL BLOCK RANDOM
FJ-1193 - PEACEFUL 1X1	FJ-1262 - GRAND 1X2	FJ-897 - MAJESTIC BLOCK RANDOM
FJ-1197 - MAJESTIC 1X1	FJ-1293 - PEACEFUL 1X2	FJ-898 - SILENT BLOCK RANDOM
FJ-1198 - SILENT 1X1	FJ-1297 - MAJESTIC 1X2	FJ-899 - MISTY BLOCK RANDOM

Conditions: New tiles sent to TILE INSTITUTE of AMERICA in sealed manufacturer's boxes from client above and selected at random.

## Report of Test

### STAIN RESISTANCE (T-72)

Standard Test Method for Stain Resistance of Ceramic Tile. This method provides the means for establishing whether this tile can resist staining from six commonly used materials, which may appear in tile specifications. The tile samples were prepared as per specifications with the common household materials (each material having one sample covered with a Petri dish and the other uncovered) and left for 24 hours, and then cleaned with Ajax Industrial Cleaner and water.

### Observation of Surface Stain

Sample Tiles	Staining Materials	Uncovered	Covered
1.	Coca Cola	No Stain	No Stain
2.	Lemon Juice	No Stain	No Stain
3.	Mustard	No Stain	No Stain
4.	Bacon Grease	No Stain	No Stain
5.	Catsup	No Stain	No Stain
6.	Wesson Oil	No Stain	No Stain

**Requirements:** When tested as described. No evidence of any surface stain remaining, and all traces of the staining materials can be washed from the tile's surface.

Test Results: **Pass**

Sincerely,

A handwritten signature in black ink that reads "Gerald M. Halweg". The signature is written in a cursive style with a large, stylized initial "G".

Gerald M. Halweg, CTC, CSI, FTA. Date: July 1, 2021  
President/CEO of TILE INSTITUTE of AMERICA